

# 7 for 28 COLOR-CRETE

## ADMIXTURE FOR COLOR CONDITIONED CONCRETE

### DESCRIPTION

7 FOR 28 COLOR-CRETE is a concentrated color admixture packaged in convenient, water-soluble, plastic bags. With the 7 standard pigments the installer can achieve 28 different shades by varying the number of bags per yard of concrete.

### PRIMARY APPLICATIONS

The primary applications are cast-in-place, slab on grade, precast, tilt-up, concrete pavers and roof tiles. 7 FOR 28 COLOR-CRETE can also be used in concrete curbing, stucco, cast stone and plaster. Perfect for providing a base color to stamped concrete, 7 FOR 28 COLOR-CRETE can also be used with a multitude of finishing techniques, such as broom finish, sponge finish, sand blast, and others, providing a limitless array of decorative finishes.

### TECHNICAL INFORMATION

7 FOR 28 COLOR-CRETE is composed of the highest grades of materials available. The synthetic Iron Oxide pigments used are specifically chosen for high tinting strength and uniform color while exceeding ASTM C979 specifications for integrally colored concrete. All colors are light-fast, lime-proof and totally weather proof, providing permanent colorfast structures.

### PACKAGING

7 for 28 COLOR-CRETE is packaged in 2-ply, 6 lb plastic bags. The inner bag is water-soluble and may be thrown into the concrete mixer. Each bag contains a precise measurement of pigment and are added directly to Ready-Mix drums eliminating waste and human error.

### SHELF LIFE

7 for 28 COLOR-CRETE Powder: Unlimited, as long as packaging is undamaged and intact.

### PRECAUTIONS/LIMITATIONS

Consult Increte's Best Practices Guide for Integrally Colored Concrete

### SPECIFICATIONS/COMPLIANCES

Meets or exceeds ASTM C-979 requirements



Decorative Concrete  
Technology

### INCRETE SYSTEMS

1611 Gunn Hwy. Odessa, FL 33556

Phone: 813-886-8811 - Toll-Free: 800-752-4626 - Fax: 813-920-1516

[www.increte.com](http://www.increte.com)

A Division of The Euclid Chemical Company An **RPM** Company

# 7 for 28 COLOR-CRETE

## ADMIXTURE FOR COLOR CONDITIONED CONCRETE

### DIRECTIONS FOR USE

#### MIX DESIGN

Use a minimum cement content of 470 pounds per cubic yard (5-bag mix). Aim for the lowest slump that can be placed and finished readily. Adding extra water to increase slump may cause excessive bleeding and non-uniformity in color. Do not use any admixtures that contain calcium chloride. Calcium Chloride will cause uneven color, discoloration, and salt deposits.

Due to variation of job site conditions and materials, make a job site sample that requires at least 3 cubic yards of concrete. Use the same mix design, raw materials, and placement and finishing techniques that will be used on the job. Special color blends to match existing structures or specific color needs are available in batch-size packages.

#### BATCHING AND MIXING

Use a minimum cement content of 470 pounds per cubic yard. Cement substitutes, such as flyash or slag, should not be used unless Increte is consulted for suggestions. If a cement substitute is used, it must be added to all mixes on the project having the same color. (Cement Substitutes like Fly Ash & Slag can affect the final color) Do not exceed a 5" slump. Ideally, the best mixing procedure is to batch 40%-50% of the load. With the mixer running add the color and mix for 1-2 minutes before adding the balance of materials. Once the balances of materials have been added, mix the drum at mixing speed for five minutes. Be sure to use the same mix design and slump from truck to truck. (If higher slump is required it may be obtained by the use of water reducing admixtures) It is important to use the same cement as different cements can have different shades of gray that can affect the final color. Watch the slump closely as varying slumps is an indication of varying water to cement ratios and this can affect the final color. Never add 7 for 28 COLOR-CRETE to an empty drum/mixer.

#### FORMING & PLACING CONCRETE FOR VERTICAL SURFACES

Seal joints in forms for vertical surfaces. Water leakage at joints causes changes in water-cement ratio and discoloration near the leak. Use a non-staining form release agent and thoroughly clean forms before reusing them. Remnant cement from dirty forms can stain colored surfaces. Do not allow heads of internal vibrations to touch the forms. This will cause dark spots called vibrator burns.

It may be necessary to precondition new natural grain wood forms before they are used on the job. This can be done by coating them with cement slurry containing the pigment to be used, then removing the coating.

#### FINISHING & CURING FLATWORK

Do not start finishing colored concrete until the bleed water has evaporated. Finishing too early causes discoloration and a weak, non-durable surface.

Use mechanical float or trowel if possible. The one-way motion of the blade creates a more uniform colored surface than the back and forth motion used in hand finishing. Move edgers in one direction only to produce a more uniform color.

Concrete in the sun sets at a different rate than concrete in the shade. This may cause differences in color. If possible, time the pour to avoid having sunlit and shaded areas. Do not add water to the surface during finishing operations. Added water may create a blotchy surface.

For a uniform color and consistent cure consider the use of one of Increte Systems Cure and Seal products.

**WARRANTY** All recommendations, statements and technical data contained herein based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his use of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person having any injury, loss or damage directly or indirectly resulting from use of or inability to use the product. Recommendations or statements other than those contained in written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

**IMPORTANT NOTICE:** THESE PRODUCTS ARE SOLD SUBJECT ONLY TO THE EXPRESSED WARRANTIES CONTAINED HEREIN. ADDITIONAL WARRANTIES, EXPRESSED OR IMPLIED, AND ANY WARRANTY OF MERCHANT ABILITY IS HEREBY EXCLUDED. BUYER AGREES THAT SELLER ASSUMES NO LIABILITY FOR CONSEQUENTIAL DAMAGES OF ANY KIND, WHICH RESULT FROM THE USE OR MISUSE OF THE MERCHANDISE SOLD HEREUNDER. IN THE EVENT THAT THE BUYER PROVES THAT ANY GOODS RECEIVED DO NOT CONFORM TO THE SPECIFICATIONS AGREED TO BETWEEN THE PARTIES OR IF THE BUYER PROVES THAT SUCH GOODS WERE DEFECTIVELY MANUFACTURED. THE BUYER'S REMEDIES SHALL BE LIMITED TO EITHER THE RETURN OF THE GOODS AND REPAYMENT OF THE PURCHASE PRICE OR REPLACEMENT OF THE NON-CONFORMING GOODS AT THE OPTION OF THE SELLER. SUCH REMEDY BEING EXCLUSIVE OF ALL OTHERS AND THE SOLE REMEDY AVAILABLE TO THE BUYER, HEREBY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.